



exclusive wallcovering

VINYL WALLCOVERING	
Type II (Fed. Spec. CCC-W-408A)	Fire Testing NFPA 255 / ASTM E-84 Tunnel Test: Class A Flame Spread 20 Smoke Developed 40 NFPA 286 Corner Burn Test: Meets requirements for Flame Spread, Smoke Developed and Flashover
Width 54" (137 cm)	
Pattern Match do not reverse / straight match	
Weight 21 oz/ly (651 g/lm)	
Backing non-woven	

© 2008 Wall Source LLC

Product Use Advisory

This product is intended for use in buildings designed and maintained to avoid moisture accumulation on or within walls, particularly in warm, humid climates.

The features that make vinyl wallcovering cleanable and durable also render it very low in permeability. Vinyl wallcovering products should not be installed on walls that contain excessive moisture or are subject to moisture infiltration. If mold or mildew is present, or if walls show moisture damage or have excess moisture content, do not proceed with installation. Moisture infiltration and water vapor in and behind the wall must be eliminated for proper performance.

Processes that increase permeability, including microventing, should be considered for use under certain conditions. In addition, the use of a mildew inhibitor in the primer and adhesive is highly recommended. Primers and adhesives with the highest possible permeability rating are also highly recommended.

After installation, the walls and wallcovering should be monitored for potential moisture or water vapor infiltration and accumulation. Any such infiltration or accumulation after installation must be promptly eliminated.

	Made with water-based inks & coatings
	No ozone-depleting chemicals have been used
	Contains no cadmium or mercury-based pigments
	Manufactured using comprehensive raw material recycling
	High durability
	Made in the U.S.A.
	Vinyl wallcovering, by nature, is impermeable*

*This product can be microvented with the Duravent process for breathability. You may specify this as an added feature.

D.L.Couch
 DLCouch.com
 800.433.0790

please call for larger samples